SICAN	Sican Top Tint Two Tone Films									tant.
Film Type	Product code	CR	Color	Ply	Reflective	Width	VLT	IR Reject	UV Cut	Solar Energy Rejection
Top Tint Two Tone	TPSI-BK		Silver Black	2	non	50cm	0~4%	12-64%	59-99%	57~67%
	TPSI-BL		Silver Blue	2	non	50cm	3~36%	14-72%	45-93%	38~59%
	TPSI-GN		Silver Green	2	non	50cm	1~38%	15-80%	44-95%	42-68%
	TPSI-RD		Silver Red	2	non	50cm	2~62%	13-56%	62-73%	37-54%
	TPGN-BK		Green Black	2	non	50cm	0~4%	15-86%	99.00%	55-85%
	TPBL-BK		Blue Black	2	non	50cm	1~38%	14-75%	67-99%	55-75%
	TPRD-BK		Red Black	2	non	50cm	2~5%	14-86%	68-99%	54-86%
	TPGD-BK		Gold Black	2	non	50cm	0~4%	13-80%	60-99%	55-70%
	TPBK-S		Black (sun strip)	2	Reflective	20cm	0~4%	94%	97-99%	88-92%
	TPGD-S		Gold (sun strip)	2	Reflective	20cm	0~4%	90%	83-95%	74-78%
	TPGN-S		Green (sun strip)	2	Reflective	20cm	0~5%	94%	93-99%	88-90%
	TPBL-S		Blue (sun strip)	2	Reflective	20cm	0~5%	94%	96-99%	86-89%
	TPRD-S		Red (sun strip)	2	Reflective	20cm	2~5%	94%	93-97%	88-90%
	ТРВК		Black (sun strip)	2	Non	20cm	13~76%	11%	12-54%	31-52%
	TPBL		Blue (sun strip)	2	Non	20cm	6~72%	11%	1-47%	25-42%
	TPGN		Green (sun strip)	2	Non	20cm	29~78%	11%	1-44%	22-42%

*Above colors are for reference only, figures are laboratory test results, actual production may vary from batch to batch

FEATURES

--- Variety colors in gradation style

--- Non anti-scratch, if anti-scratch is needed, please specified in the order

HIGHLIGHTS

Suitable on the side windows and rear window, Top Tine Two Tone is a series of gradation automotive films. Variety in different colors and styles, it shows personal taste and character. Cool in heat control with an awesome sensation.