



Sican Premium Films Non-Reflective Automotive



Film Type	Product Code	CR	Color	Ply	Reflective	VLT	IR Reject	UV Cut	Interior Reflection	Exterior Reflection	Solar Energy Rejection
Premium Film - Non Reflective	KRC-CH01	■	Charcoal	1	Non	2%±1%	14%	99%	N/A	N/A	N/A
	KRC-CH05	■	Charcoal	1	Non	5%±1%	14%	99%	N/A	N/A	N/A
	KRC-CH15	■	Charcoal	1	Non	13%±2%	12%	99%	N/A	N/A	N/A
	KRC-CH35	■	Charcoal	1	Non	35%±4%	11%	99%	N/A	N/A	N/A
	KRC-CH50	■	Charcoal	1	Non	50%±5%	11%	99%	N/A	N/A	N/A
	PRC-BK05	■	Super Dark BK P	1	Non	5%±1%	14%	99%	N/A	N/A	N/A
	PRC-BK15	■	Dark BK P	1	Non	13%±2%	12%	99%	N/A	N/A	N/A
	PRC-BK25	■	BK P	1	Non	25%±3%	12%	99%	N/A	N/A	N/A
	PRC-BK32	■	Light BK P	1	Non	32%±4%	11%	99%	N/A	N/A	N/A
	PRC-BK50	■	L. L. BK P	1	Non	50%±5%	12%	99%	N/A	N/A	N/A
	ATRH-BK01P	■	Ultra S. D. BK P	2	Non	2%±1%	14%	99%	3.8%	4.4%	55%
	ATRH-BK05P	■	Super Dark BK P	2	Non	5%±1%	14%	99%	5.1%	3.3%	54%
	ATRH-BK15P	■	Dark BK P	2	Non	13%±2%	12%	99%	4.2%	4.7%	48%
	ATRH-BK32P	■	Light BK P	2	Non	32%±4%	11%	99%	5.0%	3.2%	39%
	ATRH-BK50P	■	L. L. BK P	2	Non	50%±5%	12%	99%	4.7%	3.8%	37%
	ATRH-BK01	■	Ultra S. D. BK	2	Non	2%±1%	14%	99%	3.8%	4.4%	55%
	ATRH-BK05	■	Super Dark BK	2	Non	5%±1%	14%	99%	5.1%	3.3%	54%
	ATRH-BK15	■	Dark BK	2	Non	13%±2%	12%	99%	4.2%	4.7%	48%
	ATRH-BK32	■	Light BK	2	Non	32%±4%	11%	99%	5.0%	3.2%	39%
	ATRH-BK50	■	L. L. BK	2	Non	50%±5%	12%	99%	4.7%	3.8%	37%

*Above colors are for reference only, figures are laboratory test results, actual production may vary from batch to batch

HIGHLIGHTS

With tough coating surface, all the films are scratch resistant. Cut down harmful UV, with great total solar heat control. 1 or 2 PLY non-reflective.

FEATURES

- 1PLY or 2 PLY
- All Anti Scratch
- No metal & non-reflective

